



INSTITUTO
EDUARDO
TORROJA

**INSTITUTO DE CIENCIAS
DE LA CONSTRUCCIÓN
EDUARDO TORROJA**

C/ Serrano Galvache n. 4. 28033 Madrid (Spain)
Tel.: (34) 91 302 04 40 / Fax: (34) 91 302 07 00
direccion.ietcc@csic.es www.ietcc.csic.es



European Technical Assessment

ETA 06/0089
of 28/ 02/ 2018

English translation prepared by IETcc. Original version in Spanish language

General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) Nº305/2011:

Instituto de Ciencias de la Construcción Eduardo Torroja (IETcc)

Trade name of the construction product

Sistema COTETERM

Product family to which the construction product belongs

External Thermal Insulation Composite System with rendering for use on building walls

Manufacturer

PAREX Morteros S.A.U.

C/ Italia 13-21. Polígono Industrial Pla de Llerona. 08520 Las Franquesas del Vallés (Barcelona) – Spain

Manufacturing plant(s)

C/ Italia 13-21. Polígono Industrial Pla de Llerona. 08520 Las Franquesas del Vallés (Barcelona) – Spain.

Camino de Yuncillos s/n. 45520 Villaluenga de la Sagra (Toledo). Spain.

Camino de la mortera. Pol. Ind. La estacada. 24750 La Bañeza, Leon. Spain

Pol. Ind. Mos del Bou, Parcela 14b, 03340 Albufera, Alicante. Spain

This European Technical Assessment contains

9 pages.

Annex 1. Contain confidential information and is not included in the ETA when that assessment is publicly available.

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of

Guideline for European Technical Approval (ETAG) nº 004 ed. 2013, used as European Assessment Document (EAD)

This version replaces

ETA 06/0089 issued on 02/ 09/ 2011

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission according to Article 25 Paragraph 3 of Regulation (EU) No 305/2011.

SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of the product

The External Thermal Insulation Composite System (from now on, referred to as ETICS) "COTETERM" is designed and installed in accordance with the manufacturer, design and installation instructions, deposited at the IETcc⁽¹⁾.

It is made up on site from these components. The manufacturer is ultimately responsible for the ETICS COTETERM which is a bonded system with supplementary mechanical fixings with EPS and XPS panel and mechanically fixed ETICS with supplementary adhesive on MW panel, the minimum number of fasteners per square metres are 6 for EPS/ XPS and MW².

This ETICS comprises the following components, which are factory produced by the manufacturer or a supplier.

	Components	Consume kg/m ²	Thickness [mm]
Insulation material with associated method of fixing	COTETERM Panel EPS : Bonded Board of Expanded polystyrene (EPS) (EN 13163) with supplementary mechanical fixings (minimum 6 fasteners/m ²)	0,7- 4.0	30 - 250
	COTETERM Panel XPS .: Bonded Board of Extruded polystyrene (XPS) (EN 13164) with supplementary mechanical fixings (minimum 6 fasteners/m ²)	3,30-40,0	30 – 250
	COTETERM Panel MW : Mechanically fixed Mineral wool (MW) (EN 13162) with supplementary adhesive (minimum 6 fasteners/m ²) ²	120 y 70	50-100
	Adhesive: COTETERM[®]-M . Minimum bonded surface: 60% for EPS/XPS and 80% for MW. (cement based mortar in powder requiring addition and mixing with 18,0 ± 1,0% water.	1,2-1,4 per mm thickness	5,0-10,0
Base coat	COTETERM[®]-M COTETERM[®]-IMPACT COTETERM[®]-LG (only for EPS) and with finishing coat: ACRYLIC, ACABADO, CALCIFIN.	1,2-1,4 per mm thickness	3.0-5.0
Glass fibre mesh	COTETERM MALLA STD 167[™] : Standard glass fibre alkali resistant mesh COTETERM MALLA ANTIVANDALICA 275 2C . Reinforced glass fibre alkali resistant mesh	----	0,5
Primer coat	COTETERM[®] FONDO . Acrylic binder based primer requiring addition of 30 % of water, foreseen to be applied in two layers before COTETERM ACABADO or COTETERM ACRYLIC/ AQUASOL COTETERM ANITFISURAS PRIMER Acrylic binder based primer before COTETERM ANTIFISURAS LISO COTETERM SK Silicate paint . Silicate binder based primer before CALCIFIN	2 m ² / litre per layer 5 m ² /litre 7 m ² litre	--
Finishing coat	COTETERM[®] ACABADO GR (1.7 mm). Polymeric binder based ready to use paste	3-4	2.5-3
	COTETERM[®] ACRYLIC (1.1 mm), COTETERM[®] ACRYLIC MD (2.0 mm), COTETERM[®] ACRYLIC SLX (1.1 mm), COTETERM[®] ACRYLIC RPB (1.0 mm). Acrylic binder based ready to use paste	2.0-3.0	1.5-2 RPB 3-5
	COTETERM[®] ESTUCO FLEXIBLE (CEF ESTUCO) COTETERM[®] ESTUCO FLEXIBLE SILEX (CEF SILEX) . Mineral stucco finishing coat powder requiring addition of 5,3 ± 0,2 litres of water per bag CEF ESTUCO y 4.7± 0,2 litres of water per bag CEF SILEX. The coat is applied without any primer.	2.0-3.0	1.5-2
	AQUASOL . Polymeric binder based ready to use paste	1.5-2.5	1-1.5
	CALCIFIN . Mineral lime plaster powder requiring addition of 6.8 ± 0,2 litres of water per bag It is applied only with primer COTETERM SK Silicate paint	1.8-2.2	1.5
	COTETERM ANITFISURAS LISO . Polymeric binder based ready to use paste. It is applied only with COTETERM ANITFISURAS PRIMER	2.2 m ² /litre per layer	Aprox 2 mm
	COTETERM ANCLAJE, COTETERM ANCLAJE STRU 2G, COTETERM ANCLAJE NTK U, COTETERM ANCLAJE H1, COTETERM ANCLAJE H3 . Plastic anchors (expansion element and sleeve) for insulation material with different lengths (60 or 90 mm) in relation with thickness of insulation board	Remain under the manufacturer responsibility	
Ancillary elements	Aluminium profiles : Base, corners, top and window sills, and its fixing devices LANKO[®] 603 PU FLEX . One component polyurethane mastic		

2 Specification of the intended use in accordance with the applicable EAD

This ETICS is intended to be used as external thermal insulation for building walls. The walls are made of masonry (bricks, blocks...), or concrete (cast on site or as prefabricated panels) with a reaction to fire classification A1 to A2-s2,d0 according to EN 13501-1 or A1 according to the EC decision 96/603/EC as amended. The ETICS is designed to give the wall to which is applied satisfactory thermal insulation.

(1) The technical documentation of this European Technical Assessment is deposited at the *Instituto de Ciencias de la Construcción Eduardo Torroja* (IETcc) and, as far as relevant for the tasks of the approved bodies involved in the attestation of conformity procedure, is handed over to the approved bodies.

(2) The numbers of fasteners used with MW must comply with the National requirements.

This ETICS is made of non load-bearing construction elements. It does not contribute directly to the stability of the wall on which is installed, but it can contribute its durability by providing enhanced protection from the effect of weathering. The minimum thermal resistance of the ETICS shall be $\geq 1,0 \text{ m}^2\text{K/W}$.

This ETICS can be used on new or existing (retrofit) vertical walls. It can also be used on horizontal or inclined surfaces which are not exposed to precipitation. The ETICS is not intended to ensure the airtightness of the building structure.

Design and installation of ETICS should take into account principles laid down in chapter 7 of ETAG 004 and shall be done in accordance with national instructions. This ETA covers application of bonded ETICS where the concrete for testing of bond strength is representative for masonry or concrete. For bonded applications onto other substrates (e.g. organic paints or ceramic tiles), testing on the job site is necessary.

The provisions made in this ETA are based on an assumed working life of 25 years as minimum, provided that the conditions laid down for the installation, appropriate use, maintenance and repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right product in relation to the expected economically reasonable working life of the works.

Installation. The ETICS is installed on site. It is the responsibility of the manufacturer to guarantee that the information about design and installation of this ETICS is effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this European Technical Assessment. Besides, all the data concerning the execution shall be clearly indicated on the packaging and/or the enclosed instruction sheets using one or several illustrations.

The wall on which the ETICS is applied shall be sufficiently stable and airtight. Its stiffness shall be large enough to ensure that ETICS is not subjected to deformations, which could lead to damage. The requirements given in ETAG 004, chapter 7 have to be considered.

Design. In any case, the user shall comply with the national regulations and particularly concerning fires and wind load resistance. Only the components described in clause 1 with characteristics according to clause 3 of this ETA can be used for this ETICS.

The works including the details (connection, joint,..) shall be designed in order to avoid water penetration behind the system. To bond the ETICS, the minimal surface area and the method of bonding shall comply with the characteristics of the ETICS as well as the national regulations. In any case, the minimal surface shall be at least 60% for EPS/XPS and 80% for MW. Besides The numbers of fasteners used with MW must comply with the National requirements

Execution. The recognition and preparation of the substrate as well as the generalities about the execution of the ETICS shall be carried out in compliance with:

- Chapter 7 of the ETAG. 004, with imperative removal of any existing paint finish or renders which may difficult the bond resistance of the system.
- Corresponding national regulations.

The particularities in execution linked to the method of bonding and the application of the rendering system shall be handled in accordance with manufacturer prescriptions. In particular it is suitable to comply with the quantities of rendering applied, the thickness regularity and the drying periods between layers.

Use, maintenance and repair of the works. It is accepted that the finishing coats shall normally be maintained in order to fully preserve the system's performance. Maintenance will include at least:

- The repairing of localised damaged areas due to accidents
- The application of various products or paints, possibly after washing or "ad hoc" preparation.

Necessary repairs should be done rapidly. It is important to be able to carry out maintenance as far as possible using readily available products and equipment, without spoiling appearance.

3 Performance of the product and references to the methods used for its assessment

The identification tests and the assessment for the intended use of this ETICS according to the Essential Requirements were carried out in compliance with the ETA Guidance n. 004: External Thermal Insulation Composite Systems with Rendering- edition February 2013 (called ETAG 004, in this ETA).

3.1 ETICS Characteristics

Mechanical resistance and stability (BWR 1). No relevant.

Safety in case of fire ((BWR 2). **Reaction to fire.**

ETICS composition		Euroclass EN 13501-1	
		EPS 60 mm/MW	XPS 80mm
Adhesive: COTETERM [®] -M		B-s1, d0	B-s2, d0
Base coat: COTETERM [®] -M // LG + Malla COTETERM [®]			
Finishing layer	COTETERM [®] FONDO + COTETERM [®] ACRYLIC		
	COTETERM [®] FONDO + COTETERM [®] ACABADO		
	COTETERM [®] ESTUCO FLEXIBLE (CEF ESTUCO)		
	COTETERM [®] FONDO + AQUASOL		
	COTETERM [®] FONDO + CALCIFIN		
COTETERM [®] FONDO + COTETERM [®] anti FISURAS		B-s2, d0	
Adhesive: COTETERM [®] -M		B-s1, d0	B-s2, d0
Base coat: COTETERM [®] -IMPACT + Malla COTETERM [®]			
Finishing layer	COTETERM [®] FONDO + COTETERM [®] ACRYLIC		
	COTETERM [®] FONDO + COTETERM [®] ACABADO		
	COTETERM [®] ESTUCO FLEXIBLE (CEF ESTUCO)		
	COTETERM [®] FONDO + AQUASOL		
	COTETERM [®] FONDO + CALCIFIN		
COTETERM [®] FONDO + COTETERM [®] anti FISURAS		B-s2, d0	

Hygiene, health and environment (BWR 3)

Water absorption

Base coat and bade coat+ termination coat	After 1 h	After 24 h
COTETERM [®] -M	< 1 kg/m ²	<0,5 kg/m ²
COTETERM [®] - IMPACT		
COTETERM [®] - LG		
COTETERM [®] ACABADO COTETERM [®] ACABADO GR		
COTETERM [®] ANTIFISURAS LISO		
COTETERM [®] ESTUCO FLEXIBLE (CEF ESTUCO)		
COTETERM [®] ESTUCO FLEXIBLE SILEX (CEF SILEX).		
AQUASOL		
CALCIFIN		
COTETERM [®] ACRYLIC, COTETERM [®] ACRYLIC MD, COTETERM [®] ACRYLIC SLX, COTETERM [®] ACRYLIC RPB		0,6 kg/m ²

Hygrothermal behaviour. It has been assessed on eight rigs. During heat rain and heat-cold cycles, none of the following defects occurs during testing:

- Blistering or peeling of any finishing.
- Failure or cracking associated with joints between insulation product boards or profiles fitted with system.
- Detachment of render.
- Cracking allowing water penetration to the insulation layer.

This system is therefore assessed as resistant to hygrothermal cycles.

Freeze / thaw behaviour. The water absorption of base coat and most of rendering system is less than 0.5 kg/m² after 24 hours and so the system can be assessed as freeze/thaw resistant without any further testing. The test was performed on COTETERM ACRYLIC RPB with satisfactory results

Water vapour permeability

Equivalent air thickness	
ETAG 004 requeriments	Sistema COTETERM
≤ 2 m (EPS) // ≤ 1 m (MW)	≤ 1 m

Dangerous substances. This system complies with the provisions of Guidance Paper H⁽³⁾. A declaration of conformity in this respect was made by the manufacturer. In addition to the specific clauses relating to dangerous substances contained in this ETA, there may be other requirements applicable to the ETICS falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the EU Regulations 305/11, these requirements need also to be complied with, when and where apply.

(3) *Guidance Document H: "A harmonized approach related to dangerous substances under the Construction Products Directive".*
ETA 06/0089 of 28/02/2018 – page 5 of 9

Impact resistance. The resistance to hard body impacts (3 and 10 Joules) tests carried out on samples of systems compositions lead to the following categories according to the insulation boards and the mesh used:

Insulation	Base coat	Termination coat	Std 167	275 2C
EPS / XPS / MW	COTETERM [®] -M	COTETERM [®] ACABADO COTETERM [®] ACABADO GR	II	I / II / I
		COTETERM [®] ACRYLIC, COTETERM [®] ACRYLIC MD, COTETERM [®] ACRYLIC SLX, COTETERM [®] ACRYLIC RPB	II / III / II	I / III / I
		COTETERM [®] ESTUCO FLEXIBLE (CEF ESTUCO) and COTETERM [®] ESTUCO FLEXIBLE SILEX (CEF SILEX).	II	I
		AQUASOL	II	II / II / I
		CALCIFIN	II	II
	COTETERM [®] -IMPACT	COTETERM [®] ANTIFISURAS LISO	II	II
		COTETERM [®] ACABADO COTETERM [®] ACABADO GR	I	I
		COTETERM [®] ACRYLIC, COTETERM [®] ACRYLIC MD, COTETERM [®] ACRYLIC SLX, COTETERM [®] ACRYLIC RPB	I	I
		COTETERM [®] ESTUCO FLEXIBLE (CEF ESTUCO) and COTETERM [®] ESTUCO FLEXIBLE SILEX (CEF SILEX).	I	I
		AQUASOL	I	I
EPS	COTETERM [®] -LG	CALCIFIN	II / I / I	I
		COTETERM [®] ANTIFISURAS LISO	I	I
		COTETERM [®] ACABADO COTETERM [®] ACABADO GR	III	III
		COTETERM [®] ACRYLIC, COTETERM [®] ACRYLIC MD COTETERM [®] ACRYLIC SLX COTETERM [®] ACRYLIC RPB	III	III
		CALCIFIN	II	III

Safety in use (BWR 4)

Bond strength: Base coat onto insulation board. The tests were performed on samples of EPS, XPS, and MW insulation boards faced with base coat, and were subjected to the following tests, and in all cases breakage location was 100% on insulation:

Bond Strength results (MPa)		
Thermal insulation	Initial state	After hygrothermal cycles (on rigs)
EPS	≥ 0,08	≥ 0,08
XPS	≥ 0,08	≥ 0,08
MW	0,005	0,005

Bond strength: Adhesive onto insulation board. The tests were performed on samples of EPS, XPS and MW insulation boards faced with base coat, and were subjected to the following tests, and in all cases breakage location was 100% on insulation:

Adhesive onto insulation board (MPa)			
Thermal insulation	Initial state	Immersion 48 h and 2 h drying	Immersion 48 h and 7 d drying
EPS	≥ 0,08	≥ 0,08	≥ 0,08
XPS	≥ 0,08	≥ 0,08	≥ 0,08
MW	0,005	0,005	0,005

Bond strength: Adhesive onto concrete

Bond Strength results on concrete (MPa)		
Initial state	Immersion 48 h and 2 h drying	Immersion 48 h and 7 d drying
≥ 0,25	≥ 0,08	≥ 0,25

The minimal bonded surface S, which shall exceed 40%, is calculated as follows: $S (\%) = [0,03 * 100] / B$
Where: B: minimum mean failure resistance of the adhesive to the insulation product in dry conditions expressed in MPa and 0,03 MPa correspond to the minimum requirements.

Displacement test of the fasteners. NPA since the bonded area exceeds 20 %

Pull-through of the fasteners

Values (N/ fastener)	Dry conditions	Wet conditions
Minimal	232	182
Mean	365	229

The mineral wool used in the test has 6 cm of thickness with a TR≥5,0. The test results are also valid for: Insulation product of the same type with higher thickness and/or higher tensile strength perpendicular to the faces and Anchors with the same or larger plate diameter and/or the same or higher plate Stiffness (see EOTA Technical Report n° 26).

Protection against noise (BWR 5). NPA

Energy economy and heat retention (BWR 6)

Thermal resistance. The additional thermal resistance R_{ETICS} provided by the ETICS to the substrate wall is calculated in accordance with EN ISO 6946 from the nominal value of the insulation product's thermal resistance R_D given accompanied to the CE marking and from the thermal resistance of the rendering system R_{render} which is about 0,02 m²K/W.

$$R_{ETICS} = R_D + R_{render}$$

The thermal bridges caused by mechanical fixing devices influence the thermal transmittance of the entire wall and shall be taken into account using the following calculation:

$$U_c = U + \Delta U \text{ (W/m}^2\text{K)},$$

U_c : Corrected thermal transmittance (W/(m².K)) of the entire wall,, including thermal bridges.

U : thermal transmittance of the entire wall, including ETICS, without thermal bridges) (W/(m².K):

$$U = \frac{1}{R_i + R_{render} + R_{substrate} + R_{se} + R_{si}}$$

R_i : thermal resistance of the insulation product // R_{render} :thermal resistance of the render (about 0,02 (m².K)/W).

$R_{substrate}$: thermal resistance of the substrate of the building (concrete,brick...)((m².K)/W) //

R_{se} : external superficial thermal resistance ((m².K)/W) // R_{si} : internal superficial thermal resistance ((m².K)/W).

ΔU : Correction term of the thermal transmittance for mechanical fixing devices

$$\Delta U = X_p \cdot n,$$

n : number of anchors (through insulation product) per m² // X_p :point thermal transmittance value of the anchor (0.002 W/K).

Aspect of durability and serviceability

Bond strength after ageing. In all cases breakage location was 100% on EPS, XPS and MW:

Rendering system (base coat + finishing coat)	Thermal insulation	After Hygrothermal cycles (rigs) (MPa)	After freeze/thaw cycles (samples) (MPa)
COTETERM*-M + any finishing coat	EPS	≥ 0,08	-----
	XPS		-----
COTETERM*-IMPACT + any finishing coat	MW	0,005	-----
COTETERM*-LG + any finishing coat	EPS	≥ 0,08	-----

3.2 Characteristics of the components

Detailed information on the chemical composition and other identifying characteristics of the components, following Annex C of ETAG 004, has been deposited at the IETcc. Further information can be observed from the product data sheets, which are part of the Technical Documentation for this ETA.

Insulation product. Factory–prefabricated, uncoated boards made of EPS /ESP-G, XPS and MW, having the description, characteristics and performances (as minimum) defined in the table below:

Characteristics	Standard	EPS	MW	XPS
Reaction to fire Euroclass	EN 13501-1	E	A1	E
Length (mm) / Tolerance type	EN 822	1000 / L2	1200	1250
Width (mm) / Tolerance type	EN 822	500-600/ W2	600	600
Thickness (mm) / Tolerance type	EN 823	30-250 / T1	50-240 / T5	T1
Squareness	EN 824	S2	-----	-----
Flatness	EN 825	P5	≤ 6 mm/m	-----
Thermal conductivity a 10 °C (W/m.K)	EN 12667 o EN 12939	CE		
Dimensional stability under Temperature and humidity specific conditions (DS 90/70) %	EN 1604	< 2	< 1	< 1
Tensile strength perpendicular to faces in dry conditions (N/mm ²)	EN 1607	≥ TR 80	≥ TR 5,0	≥TR200
Water absorption ((partial immersion) (kg/m ²)	EN 1609	< 1	< 1	< 1
Water vapour diffusion (μ)	EN 12086	20 - 100	1	60-150
Shear strength (N/mm ²)	EN 12090	≥ 0,02	-----	≥ 0,02
Shear modulus (N/mm ²)	EN 12090	≥ 1	-----	≥ 1

Render. Render strip tensile resistance: No Performance Assessment.

Glass fibre mesh. Tearing strength after ageing of the glass fibre mesh was tested according ETAG 004:

Status	Units	Malla COTETERM / Antivandalica	
		Warp direction	Weft direction
Initial	N / mm	≥ 20	
After ageing	N / mm	≥ 20	
	Residual Resistance (%)	≥ 50	

Fasteners. Fastener with CE marking with ETA n° 14/0130 y 04/0023. The plate has Ø60 mm in and the plate Stiffness is 0,5 kN/mm².

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

System of attestation of conformity. According to the decision 97/556/EC of the European Commission ⁽⁴⁾ amended by 2001/596/EC ⁽⁵⁾ the system of assessment and verification of constancy of performance (see Annex V to Regulation (EU) n° 305/2011) given in the following table applies.

Product	Intended uses	Level or Classes	System
COTETERM	External Thermal Insulation Composite System with rendering for use on building walls	Any	2+

This system of attestation of conformity +2 is defined as follows:

Tasks for the manufacturer: Initial type-testing of the product, Factory production control and Testing of samples taken at the factory in accordance with a prescribed test plan.

Tasks for the notified body: Certification of factory production control on the basis of:

- o Initial inspection of factory and of factory production control.
- o Continuous surveillance (annual), assessment and assessment of factory production control.

5 Technical details necessary for the implementation of the AVCP system, as provided for the applicable EAD

The ETA is issued for this kit on the basis of agreed data/information, deposited at IETcc, which identifies the product that has been assessed and judged. It is the manufacturer's responsibility to make sure that all those who use the kit are appropriately informed of specific conditions according to sections 1, 2, 4 and 5 including the annexes of this ETA. Changes to the ETICS or the components or their production process, should be notified to the IETcc before the changes are introduced. IETcc will decide whether or not such changes affect the ETA and if so whether further assessment or alterations to the ETA shall be necessary.

5.1 Tasks of the manufacturer

Factory production control. The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this ETA.

The manufacturer may only use components stated in the technical documentation of this ETA including Control Plan. The incoming raw materials are subjected to verifications by the manufacturer before acceptance.

For the components of the ETICS which the manufacturer does not manufacture by himself, he shall make sure that factory production control carried out by the other manufacturers gives the guarantee of the components compliance with the ETA.

The factory production control shall be in accordance with the Control Plan⁽⁶⁾ which is part of the Technical Documentation of this ETA. The Control Plan has been agreed between the manufacturer and the IETcc and is laid down in the context of the factory production control system operated by the manufacturer and deposited at the IETcc. The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

Initial type-testing of the product. Initial type-testing carried out by the IETcc is that set out in chapter 5 of the guideline for External Thermal Insulation Composite System with rendering for use on building walls (ETAG 004). The IETcc assessed the results of these tests in accordance with chapter 6 of this Guide, as part of the ETA issuing procedure.

If the verifications underlying this ETA have been furnished on samples from the current production, these will replace the initial type-testing. Otherwise the necessary initial type-testing shall be carried out according to the provisions of the test plan and observance of the required property values shall be ascertained by the notified body. After changing the production process or starting the production in another manufacturing plant the initial type-test shall be repeated.

⁽⁴⁾ Official Journal of the European Communities L229/14 of 20.08.1997

⁽⁵⁾ Official Journal of the European Communities L209/33 of 02.08.2001

⁽⁶⁾ The control plan is a confidential part of this European Technical Assessment and only handed over to the notified body involved in the procedure of attestation of conformity. See section 3.2.2.

Other tasks of manufacturer. The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in section 4 in the field of ETICS in order to undertake the actions laid down in this clause. For this purpose, the control plan shall be handed over by the manufacturer to the notified bodies involved.

For initial type - testing of the ETICS and the components the results of the tests performed as part of the assessment for the ETA shall be used unless there are changes in the production line or plant. In such cases the necessary initial type- testing has to be agreed with the IETcc.

The manufacturer shall make a declaration of conformity, stating that the ETICS is in conformity with the provisions of this ETA.

5.2 Tasks of notified bodies. The notified body shall perform:

Initial inspection of factory and of factory production control. The Notified Body shall ascertain that, in accordance with the Control Plan, the factory (in particular the employees and the equipment) and the factory production control are suitable to ensure continuous and orderly manufacturing of the components according to the specifications mentioned in clause 2 of this ETA.

Continuous surveillance, assessment and assessment of factory production control, in accordance with the provisions laid down in the control plan, at least one per year.

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report. The notified certification body involved by the manufacturer shall issue an EC Certificate of factory production control stating the conformity of the provisions of this ETA.

In cases where the provisions of the ETA and its control plan are no longer fulfilled the notified certification body shall withdraw the certificate of conformity and inform to IETcc without delay.

Issued in Madrid on 28/02/ 2018


by

Instituto de Ciencias de la Construcción Eduardo Torroja

CONSEJO SUPERIOR DE INVESTIGACIONES CIENTÍFICAS

c/ Serrano Galvache 4. 28033 Madrid (Spain).

director.ietcc@csic.es www.ietcc.csic.es



On behalf of the Instituto de Ciencias de la Construcción Eduardo Torroja

Marta M^o Castellote
Director